

CLAIMS

1. An Nb-Al alloy powder for electrolytic capacitors,
comprising particles having dendritic microstructures
5 principally containing NbAl_3 , Nb_2Al , Nb_3Al , or Nb and
matrices containing Al or eutectic structures containing at
least two selected from the group consisting of NbAl_3 , Nb_2Al ,
 Nb_3Al , and Nb, the particles being covered with dielectric
layers when the powder is processed into an anode of an
10 electrolytic capacitor, the matrices surrounding the
dendritic microstructures.

2. The powder according to Claim 1, wherein the Nb-Al
alloy has an aluminum content of 46% to 90% on a mass basis,
the dendritic microstructures principally contain NbAl_3 , and
15 the matrices contain Al.

3. The powder according to Claim 1, wherein the Nb-Al
alloy has an aluminum content of 27% and more, and less than
46% on a mass basis, the dendritic microstructures
principally contain NbAl_3 , and the eutectic matrices contain
20 NbAl_3 and Nb_2Al .

4. The powder according to Claim 1, wherein the Nb-Al
alloy has an aluminum content of 14% and more, and less than
27% on a mass basis, the dendritic microstructures
principally contain Nb_2Al , and the eutectic matrices contain
25 NbAl_3 and Nb_2Al .

5. The powder according to Claim 1, wherein the Nb-Al alloy has an aluminum content of 10% and more, and less than 14% on a mass basis, the dendritic microstructures principally contain Nb₃Al, and the eutectic matrices contain Nb₃Al and Nb₂Al.

6. The powder according to Claim 1, wherein the Nb-Al alloy has an aluminum content of 10% and less on a mass basis, the dendritic microstructures principally contain Nb, and the eutectic matrices contain Nb₃Al and Nb, or the matrices principally contain Nb₃Al.

7. The powder according to any one of Claims 1 to 6, wherein the Nb-Al alloy contains at least one element selected from the group consisting of tantalum, titanium, hafnium, zirconium, molybdenum, barium, strontium, and boron.

8. The powder according to Claim 7, wherein the element content is 3% and less on a mass basis.

9. The powder according to any one of Claims 1 to 6, wherein the Nb-Al alloy contains 100 ppm and less of an iron impurity.

10. The powder according to any one of Claims 1 to 9, wherein the dendritic microstructures have a width of 3 μm and less.

11. An electrolytic capacitor comprising an anode prepared by sintering the powder according to any one of Claims 1 to 10.

12. A method for manufacturing an Nb-Al alloy powder including particles that are covered with dielectric layers when the powder is processed into an anode of an electrolytic capacitor, the method comprising a step of
5 quenching a molten Nb-Al alloy having an aluminum content of 27% to 90% on a mass basis to form particles or thin sheets having dendritic microstructures with dendrite arm spacing of 3 μm and less.

13. The method according to Claim 12, wherein the molten
10 Nb-Al alloy is quenched at a rate of 10^3 °C/sec and more.

14. The method according to Claim 12 or 13 further comprising a step of pulverizing the thin sheets.